

**AMENDMENTS TO THE CLAIMS**

The following listing of claims replaces all prior versions of claims in the application.

1. (Original): A curable resin composition

which comprises a polyoxyalkylene polymer (a) containing at least one reactive silyl group in each molecule, 5 to 50 parts by weight of a hydrocarbon-based plasticizer (b) per 100 parts by weight of (a) and 10 to 200 parts by weight of a needle crystal filler (c) on the same basis.

2. (Original): The curable resin composition according to Claim 1

which contains 20 to 40 parts by weight of the hydrocarbon-based plasticizer (b) per 100 parts by weight of the polyoxyalkylene polymer (a) containing at least one reactive silyl group in each molecule.

3. (Currently amended): The curable resin composition according to Claim 1 [[or 2]]

wherein the hydrocarbon-based plasticizer (b) is a paraffin-based hydrocarbon.

4. (Original): The curable resin composition according to Claim 3

wherein the hydrocarbon-based plasticizer (b) is a cycloparaffin-based hydrocarbon or an isoparaffin-based hydrocarbon.

5. (Currently amended): The curable resin composition according to ~~any of Claims 1 to 4~~ claim 1

wherein the needle crystal filler (c) is selected from the group consisting of sepiolite, asbestos, wollastonite, a needle crystal-type calcium carbonate, glass fiber, carbon fiber and organic fiber.

6. (Original): The curable resin composition according to Claim 5

wherein the needle crystal filler (c) is a needle crystal-type calcium carbonate.

7. (Currently amended): The curable resin composition according to ~~any of Claims 1 to~~  
~~6~~ claim 1

wherein the reactive silyl group of the polyoxyalkylene polymer (a) containing at least one reactive silyl group in each molecule is an alkoxysilyl group.

8. (Currently amended): The curable resin composition according to ~~any of Claims 1 to~~  
~~7~~ claim 1

wherein the extrudability thereof is not less than 200 g/minute and the initial fixability thereof is not less than 180 g.